

ESLON®-DC ESD

PVC CS401AS

Static dissipative (antistatic) plastic sheets

CS401AS I  clear

ELECTRICAL

		Method		Unit	ESD-Standard
Surface resistivity	ASTM D-257	DIN 53482	IEC 60093	$\Omega/\square$	$10^6 \sim 10^7$
Electrostatic discharge	MIL B-81705B			s	< 0.1
Dielectric constant	ASTM D-150	DIN 53483	IEC 60250		3

PHYSICAL

Density	ASTM D-792	DIN 53479	ISO 1183	g/cm ³	1.40
Water absorption	ASTM D-270	DIN 53495	ISO 62A	%	0.03
Pencil hardness	JIS K5400				H
Grid adhesiveness	JIS D0202				100/100

OPTICAL

Light transmittance	ASTM D-1003		ISO 13468	%	75
Haze	ASTM D-1003		ISO 14782	%	4
Refractive index	ASTM D-542		ISO 489		1.53
Distinctness of image (DOI)	JIS K7105			%	90

MECHANICAL

Tensile strength	ASTM D-638	DIN 53455	ISO 527	MPa	70
Tensile elongation at break	ASTM D-638	DIN 53455	ISO 527	%	60
Flexural strength	ASTM D-790	DIN 53452	ISO 178	MPa	90
Flexural modulus	ASTM D-790		ISO 178	MPa	3100
Compressive strength	ASTM D-695		ISO 604	MPa	80
Charpy impact strength (23°C)			ISO 179-1	kJ/m ²	3.8
Notched impact strength (23°C)	ASTM D-256		ISO 180	J/m	32

THERMAL

Heat deflection temperature	ASTM D-648	DIN 53461	ISO 75	°C	63
Coefficient of linear thermal expansion	ASTM D-696		ISO 11359	mm/mm°C	7×10^{-5}
Thermal conductivity	ASTM C-177			W/mK	0.16
Specific heat	ASTM C-177			KJ/kgK	0.84 - 1.26
Heat shrinkage	JIS K6745			%	-1
Flammability	UL 94				V-0

www.eslon-dc.de

SEKISUI

SEKISUI Chemical GmbH | Roßstraße 92 | 40476 Düsseldorf | Germany
 Phone +49 (0) 211 / 36 977 0 | eslon@sekisui.de