

**ESLON®-DC ESD**

**C-PVC CS401ATM**

Static dissipative (antistatic) plastic sheets

**CS401ATM I**  clear

**ELECTRICAL**

	Method	Unit	ESD-Standard
Surface resistivity	ASTM D-257 DIN 53482	$\Omega/\square$	$10^6 \sim 10^7$
Electrostatic discharge	MIL B-81705B	s	< 0.1
Dielectric constant	ASTM D-150 DIN 53483		3

**PHYSICAL**

Density	ASTM D-792 DIN 53479	g/cm <sup>3</sup>	1.47
Water absorption	ASTM D-270 DIN 53495	%	0.3
Pencil hardness	JIS K5400		H
Grid adhesiveness	JIS D0202		100/100

**OPTICAL**

Light transmittance	ASTM D-1003	ISO 13468	%	66
Haze	ASTM D-1003	ISO 14782	%	5
Refractive index	ASTM D-542	ISO 489		
Distinctness of image (DOI)	JIS K7105		%	90

**MECHANICAL**

Tensile strength	ASTM D-638	DIN 53455	ISO 527	MPa	73
Tensile elongation at break	ASTM D-638	DIN 53455	ISO 527	%	33
Flexural strength	ASTM D-790	DIN 53452	ISO 178	MPa	105
Flexural modulus	ASTM D-790		ISO 178	MPa	3150
Compressive strength	ASTM D-695		ISO 604	MPa	
Charpy impact strength (23°C)			ISO 179-1	kJ/m <sup>2</sup>	2.1
Notched impact strength (23°C)	ASTM D-256		ISO 180	J/m	3

**THERMAL**

Heat deflection temperature	ASTM D-648	DIN 53461	ISO 75	°C	82
Coefficient of linear thermal expansion	ASTM D-696		ISO 11359	mm/mm°C	$7 \times 10^{-5}$
Thermal conductivity	ASTM C-177			W/mK	0.16
Specific heat	ASTM C-177			KJ/kgK	
Heat shrinkage	JIS K6745			%	-1.5
Flammability	UL 94				FM4910 / V-0

[www.eslon-dc.de](http://www.eslon-dc.de)



SEKISUI Chemical GmbH | Roßstraße 92 | 40476 Düsseldorf | Germany  
Phone +49 (0) 211 / 36 977 0 | [eslon@sekisui.de](mailto:eslon@sekisui.de)